



Poultry and Livestock Fabrics

FABTEX 60

Product Data Sheet

PROPERTY	TEST METHOD	Typical
Weight	ASTM D5261	6.2 oz
Material		HDPE
Color	Visual	White/Black, Black, Silver/Black
Construction	ASTM D3775	10 x 10
Thickness	ASTM D1777	9.5 Mils
Grab Tensile	ASTM D4632	150 x 145 lbs
Trapezoid Tear Strength	ASTM D4533	40 x 41lbs
Mullen Burst	ASTM D3786	220 psi

These curtains are ideal for any application where you want to prevent light penetration. To achieve total darkness it is recommended that two layers are used. To reduce temperature gain inside the building you should use the silver/black or white/black as the outer layer of the black out curtain.

Seller makes no warranty, express or implied, concerning the product furnished hereunder other than at the time of delivery it shall be of the quality and specifications stated herein. ANY IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED AND, TO THE EXTENT THAT IT IS CONTRARY TO THE FOREGOING SENTENCE ANY IMPLIED WARRANTY OF MERCHANTABILITY IS EXPRESSLY EXCLUDED. Any recommendations made by the Seller concerning uses or applications of said product are believed reliable and Seller makes no warranty of results to be obtained. This data sheet supersedes all previous data sheets for this style and is subject to change without notice. The effective date for this product data is 12/15/07.

Fabtex Solutions
Technical Department
 2556 Piney Road • Morganton, NC • 28655
 Telephone • 828 584 1240 Fax • 828 584 0880